

Tremco/Blue Ridge Fiberboard Structodek HD with Primed Red Coating

High Density Wood Fiber Roof Insulation Board with Primed Red Coating

Composition: Tremco/Blue Ridge Fiberboard Structodek HD with Primed Red Coating consists of a high density wood fiber insulation coated on 2 sides with a red primed surface coating. Tremco/Blue Ridge Fiberboard Structodek HD with Primed Red Coating is manufactured using 20% by weight of pre-consumer recycled content. Tremco/Blue Ridge Fiberboard Structodek HD with Primed Red Coating meets the requirements of ASTM C208, Type II, Grades 1 & 2.

Basic Uses: Tremco/Blue Ridge Fiberboard Structodek HD with Primed Red Coating is used as a durable roof insulation board substrate under variety of low slope BUR, MB, and Single Ply roof systems in hot and cold applied configurations. It is recommended as an overlay board for polyisocyanurate insulation. It may also be used in single or multiple layer configurations in approved roof constructions.

Limitations:

- Not intended for use under ponding conditions. Positive drainage required.
- Insulation stops are required on roofs with slopes greater than 2:12 (2" per foot).
- Not for use in direct contact with lightweight insulating concrete or recently poured gypsum decks.
- Not intended for exposure to direct flame, since board may smolder or burn. A base sheet must be hot mopped prior to any torch down MB application.

| Product Advantages | |
|-------------------------|--|
| Features | Benefits |
| High Density Wood Fiber | <ul style="list-style-type: none"> • Stable "R-Value" • Solid substrate for traffic resistance • Non-compressible substrate for improved hail resistance |
| Primed Red Coating | <ul style="list-style-type: none"> • Seals insulation surface to minimize dusting • Minimizes absorbance of single ply bonding adhesive • Compatible with membrane adhesives for strong adhesive bond |
| Code Approvals | <ul style="list-style-type: none"> • Tested for use in wide variety of roof systems • fire & uplift pressure rated assemblies |
| LEED Credits | <ul style="list-style-type: none"> • 20% Pre-Consumer Recycled Content • 6% Rapidly Renewable Content • No urea formaldehyde added • Manufactured in Danville, VA 24541 |

Size/Packaging: Tremco/Blue Ridge Fiberboard Structodek HD with Primed Red Coating is available in truckload quantities. Boards are packaged on dunnage and pallets are covered with a loose plastic shroud and banded. Standard thickness is 1/2" (13 mm).

| Board Size | SQ/pallet | Pieces/pallet | Weight/pallet |
|-----------------------------|-----------|---------------|---------------|
| 4' x 4' (1220 mm x 1220 mm) | 14.4 | 90 | 1008 lbs |
| 4' x 8' (1220 mm x 2440 mm) | 28.8 | 90 | 2016 lbs |

General Application Data: Roof replacement usually involves more complexities than new construction roofing. Often encountered are situations such as rusted/deteriorated decks, rotted wood components, rooftop equipment which cannot be moved or shut down, and numerous other conditions.

The following application information is designed to serve as a general guide. Your local Tremco Representative will prepare detailed specifications based on the condition of your roof.

Structural Decks:

Must be properly designed and structurally sound.

Drainage:

Ponding conditions are unacceptable and will adversely affect the performance of any roofing system. If positive drainage does not exist, water removal from the roof surface must be facilitated by lowering drains, and/or installing additional drains, tapered insulation, or Tremco approved lightweight concrete slope system.

Insulation Storage:

Insulation must be dry and kept dry. When stored outdoors, stack insulation on pallets at least 4 inches (100mm) above ground level. Upon receipt of insulation on the job site, cover the top and sides of the insulation with waterproof tarpaulin (not polyethylene) and secure. Do not stack more than two pallets high.

Surface Preparation: Prior to installing the insulation, the substrate must be clean, dry and free of dust, dirt, oil, or other contaminants. Concrete and gypsum decks must be properly cured and sufficiently dry prior to installing insulation.

Installation: Rows of insulation shall be offset and staggered a minimum of 2', so that the 4 corners of 4 boards do not directly connect.

Multiple Layers: The use of two separate layers of roof insulation is recommended, especially over steel decks. Two layers can minimize stress on the roof membrane which results from thermal movement of the deck. After securing the first layer of insulation, install the additional layer(s) with board joints offset a minimum 6 inches (150 mm) from the joints of the preceding layer.



Roofing & Weatherproofing Peace of Mind™

Adhesive Application: Follow application instructions for adhesive regarding priming of surfaces, if required. Tremco Low Rise Foam Insulation Adhesive is acceptable for use to adhere Tremco/Blue Ridge Fiberboard Structodek HD with Primed Red Coating.

Bitumen Application: Hot applied bitumen can be used to adhere Tremco/Blue Ridge Fiberboard Structodek HD with Primed Red Coating to concrete decks, base sheets which are mechanically attached to nailable decks, and to insulation layers(s) previously secured. Concrete decks should be primed with Tremprime WB and allowed to thoroughly dry. Adhere insulation to substrate in a full coverage of hot applied bitumen, at a coverage rate of 30 lbs. per 100 sq. ft (1.5 kg/m²) ± 20%. Place insulation immediately into the hot bitumen and step into place to achieve a solid bond.

Mechanical Fastener Application: Tremco Fasteners and Discs are recommended where mechanical attachment of the insulation is specified over steel and wood decks. Do not mix fasteners and discs of different brands unless the combination is Factory Mutual Approved. Fasteners must be driven perpendicular to the deck. Do not overdrive the fastener, as the insulation may fracture and become susceptible to loss of attachment. Fastener should be driven tight enough so that the disc will not turn.

Precautions:

User must read container labels and Material Safety Data Sheets for health and safety precautions prior to use.

Availability and Cost:

Contact your local Tremco Representative for pricing and availability. For the name and number of your Representative call the Roofing Division 216/292.5000.

Maintenance:

Your local Tremco Roofing Representative can provide you with effective maintenance procedures which may vary depending upon specific conditions. Periodic inspections, early repairs and preventive maintenance are all part of a sound roof program.

Guarantee/Warranty:

Tremco Inc. warrants Tremco/Blue Ridge Fiberboard Structodek HD with Primed Red Coating to be free of defects and to meet published physical properties when conditioned and tested according to ASTM and Tremco standards. Under this warranty, any Tremco/Blue Ridge Fiberboard Structodek HD with Primed Red Coating that is proved to be defective when applied in accordance with our written instructions and in applications recommended by Tremco as suitable for this product will be replaced with like product at no charge. THIS IS BUYER'S SOLE AND EXCLUSIVE REMEDY.

All claims concerning product defects must be made in writing within twelve (12) months of shipment. The absence of such claims in writing during this period will constitute a waiver of all claims with respect to such product.

This warranty is IN LIEU of any and all other warranties express or implied, including but not limited to, any implied warranty of MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.

Technical Services:

Your local Tremco Representative, working with the Technical Service Staff, can help analyze conditions and needs to develop recommendations for special applications. The services of the Tremco Research Center, which has earned a unique reputation in weatherproofing technology, complement and extend the services of the Tremco Technical Service staff.

| Physical Performance Characteristics | | |
|--|-------------------------------|-------------|
| Tremco/Blue Ridge Fiberboard Structodek HD with Primed Red Coating | | |
| Property | Typical Value | Test Method |
| Compressive Strength, min | 15 lbf/in ² | ASTM C165 |
| Tensile Strength Perpendicular to surface, min | 600 lbf/ft ² | ASTM C208 |
| Linear Expansion | 0.5% | ASTM C208 |
| Thermal Resistance at 75°F | R-Value = 1.3 for ½" board | ASTM C518 |
| Weight per Square | 70 lbs. per ½" board | |
| Maximum Flute Spanability | 1-5/8" for ½" board | |
| Pre-Consumer Recycled Content | 20% | |
| Rapidly Renewable Content | 6% | |

Statement of Policy and Responsibility: Tremco takes responsibility for the furnishing of quality roofing materials, and providing specifications and recommendations for their proper installation.

As neither Tremco itself nor its representatives architecture or engineering, Tremco offers no opinion on and expressly disclaims any responsibility for soundness of any structure on which its products may be applied. If questions arise as to the soundness of a structure or its ability to support a planned installation properly, the owner should obtain the opinion of competent structural engineers before proceeding. Tremco accepts no liability for any structural failure or for resulting damages and no Tremco Representative is authorized to vary this disclaimer.



3735 Green Road
Beachwood, OH 44122
216-292-5000

220 Wicksteed Ave
Toronto, ONT M4H 1G7
416-421-3300